



TECHNICAL DATA SHEET

HYDROPOLISH

PRODUCT DESCRIPTION

The Concrete Protector's Hydropolish is used to repair and maintain polished concrete with its neutral PH formula, safely removing dirt without dulling your polished concrete floors.

STANDARD COLORS: Milky White

OTHER COLORS ALSO AVAILABLE: N/A

REVISION DATE: April 10, 2024

CURE SCHEDULE (75°)

POT LIFE (1.5 GAL VOLUME) : N/A

TACK FREE (DRY TO TOUCH): 5 Min.

RECOAT OR TOPCOAT: As soon as dry

LIGHT FOOT TRAFFIC: As soon as dry

FULL CURE: 72 Hours for full repellency, 28

COVERAGE

Recommended for imparting water repellency to porous construction materials such as concrete, brick, stone, concrete blocks.

COVERAGE PER GALLON: 700-800 sq. ft. per gallon

MIX RATIO: 4 parts water: 1 part Hydropolish

RECOMMENDED FILM THICKNESS: N/A

PACKAGING INFORMATION: 1 Quart Concentrate, 1 Gallon Concentrate, 5 Gallon Concentrate

PHYSICAL PROPERTIES

FLEXURAL STRENGTH: N/A

DIAMETER: N/A

TENSILE STRENGTH: N/A

ADHESION: N/A

VISCOSITY: N/A

ABRASION RESISTANCE: N/A

ULTIMATE ELONGATION: N/A

HARDNESS: N/A

VOLATILE ORGANIC CONTENT: <100 g/l

SHELF LIFE: 1 year in unopened container

CHEMICAL RESISTANCE

N/A

LIMITATIONS

- Certain types of "Cure and Seal" products may react to the sealer causing a slight discoloration (known to react with Rez Seal).
- A blotchiness on the surface may occur during the first week or so during the curing phase (possible reaction to something in the concrete).
- Do not install on very hot days (may produce uneven-looking areas).
- Cold temps will not allow sealer to cure properly.
- Good temperature range at time of application - between 50 - 95 degrees Fahrenheit: 50 degrees Fahrenheit on the low end (with no freezing that night) and no warmer than 95 degrees Fahrenheit on the high end.

HYDROPOLISH



TECHNICAL DATA SHEET

HYDROPOLISH

BENEFITS

- Neutral PH Formula
- Low VOC
- Fast Beading Action
- Excellent Water Repellency
- Meets California South Coast AQMD Requirements
- Water-Based
- Easy to Use
- Dilutable
- Dilution Stable
- Effective at Concentrate as low as 3% Actives
- No SiH Vented Containers Required

INSTRUCTIONS

- 1) Mix product (4 parts water to 1 part Hydropolish)
- 2) Apply by spraying Hydropolish at 700-800 sq ft per gallon using pump up type sprayer and finishing with Micro Fiber pad to spread evenly. Only apply at rate to maintain a wet edge across floor. Do not puddle.
- 3) Remove any streaking with Micro Fiber pad while wet. Let cure 4-6 hours before continuing.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY:

The Concrete Protector (Division of Incredible Products, LLC), warrants that all products are assembled under rigorous quality assurance specifications and that all information supplied is exact. All information supplied is not to be taken as a warranty, but for you to conduct your own test to determine if the given product is suitable for your distinct purpose. The following list of properties should not be interpreted as specifications. CONVEYED OR SUGGESTED, NO WARRANTY IS BUILT UPON ANY DISCOVERED RESULTS OR INFORMATION YOU WILL OBTAIN DURING USE. CONVEYED OR SUGGESTED NO WARRANTY IS BUILT THAT THE GIVEN PRODUCT SHALL BE MARKETABLE OR THAT THE GIVEN PRODUCT WILL BE FIT FOR ANY DISTINCT PURPOSE. NO WARRANTY IS BUILT UPON SAID INFORMATION OR THAT THE GIVEN PRODUCT WILL NOT INFRINGE UPON ANY PATENT. The Concrete Protector is NOT liable for, direct or indirect, inadvertent or consequential damages. The Concrete Protector's liability is and will only be limited to the net selling price of our products or, at our discretion, the replacement of our products. Upon delivery of our products, your acceptance means that you accept all terms of this warranty even if other documents and or purchase orders astray from the terms of this warranty. No representative, on our behalf, is permitted to make any representation, warranty, or assume liability with any sale of our products. OUR PRODUCTS CONTAIN CHEMICALS THAT CAN CAUSE SERIOUS PHYSICAL INJURY. BEFORE THE USE OF OUR PRODUCTS, READ ALL MATERIAL AND FOLLOW ALL LISTED PRECAUTIONS TO AVOID ANY BODILY HARM.